

COMPOUND NUMBER

92410A

Description

Perfluoroelastomer (FFKM) 75 Shore A
 Black
 -15°C to 250°C

Excellent chemical resistance and good compression set.

ORIGINAL PHYSICAL PROPERTIES

		Units	Test Method
Tensile Strength	15 to 19	MPa	ASTM D412
Elongation	150 to 200	%	ASTM D412
Hardness	75 ± 5	Shore A	ASTM D2240

SEALING PROPERTIES

	25% Squeeze	Units	Time Hours	Temperature °C	Test Method
Compression Set	25 to 30	%	70	200	ASTM D395-B